

TECHNICAL DATA

COMPOSITE TAPE Product Code: **BT860T**



Description : BT860T is composed of 3 layers polyester film reinforced/laminated with polyester non-woven coated with acrylic adhesive. Excellent solvent resistant and quick grab property, tough and conformable over irregular surfaces, outstanding adhesion. CTI grade PLC=0 as Group 1 materials.

Features/benefits : The tape is made of polyester film tapes composite with non-woven fabric, and coated with yellow color rubber adhesive. It consists of materials that are represented in many UL Recognized Insulating Systems and has a UL 130°C temperature rating.

Application : Applications: 1. Winding of transformer, motor, coil, capacitor, and electric wire 2. Excellent for decorative striping 3. Edging of a wide variety of surfaces 4. Can be used as a sensing tape where automatic equipment is used in sorting, counting, or identifying roll splices and end of rolls

Technical Details :	<u>PROPERTIES</u>	<u>UNIT</u>	<u>SPECIFICATION</u>
	TOTAL THICKNESS TENSILE	mm	0.45±0.04
	STRENGTH ELONGATION	kg/25mm	30
	ADHESION TO STEEL	%	70
	DIELECTRIC BREAKDOWN	kg/25mm	0.9
	TEMPERATURE CLASS	kV	3.5
		°C	130

Test Method : In accordance with ASTM D-1000 method

Shelf Life : 6 months when storage at 23°C and 65% relative humidity

Availability : Standard 30M roll, 3" core, width 980mm

Important Notice to Purchase

All Statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed and the following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace such quantity of the product of the product proved to be defective. Neither seller nor manufacturer shall be liable for any injury loss or damage direct or consequential arising out of the use of or the inability to use the product. Before using users shall determine the suitability of the product for their intended uses and users assume all risk and liability whatsoever in connection there with.

No statement or recommendation not contained herein shall have any force or effect unless in an agreement signed by officers of Seller and manufacturer.

