TECHNICAL DATA

POYESTER FILM ELECTRICALTAPE

Product Code: BT350



91

Description :	BT350 is 0.055mm transparent polyester film tape made of a 1 mil polyester film coated with an acrylic-based adhesive system, with 0.05 mm total thickness, and recommended for a variety of coil winding, protection, and insulation applications (130°C thermal class B).		
Features/benefits :	Polyester film backing for improved moisture resistance, weight and space savings. Acrylic adhesive system designed for its resistance to solvents, freon and transformer oils. Good peel strength to paints and varnishes		
Application :	Fixing and securing non-adhesive insulating materials between layers. Fixing output wires, copper sheets or wire harnesses. Outer protective insulating wraps for bobbins, transformers, etc. Soldering protection and varied insulation uses for motors.		
Technical Details :	PROPERTIES TOTAL THICKNESS TENSILE STRENGTH ELONGATION ADHESION TO STEEL DIELECTRIC BREAKDOWN TEMPERATURE CLASS	UNIT mm kg/25mm % kg/25mm kV ℃	<u>SPECIFICATION</u> 0.055 9 70 0.6 4 130
Test Method :	In accordance with <u>ASTM D-1000</u> method		
Shelf Life :	6 months when storage at 23°C and 65% relative humidity		
Availability :	Standard 30M roll, 3" core, width 980mm		

Important Notice to Purchase

All Statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness there of is not guaranteed and the following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace such quantity of the product of the product proved to be defective. Neither seller nor manufacturer shall be liable for any injury loss or damage direct or consequential arising out of the use of or *he inability to use the product. Before using users shall determine the suitability of the product for their intended uses and users assume all risk and liability whatsoever in connection there with.



No statement or recommendation not contained herein shall have any force or effect unless in an agreement signed by officers of Seller and manufacturer.